

# QUICKLINER

## Key Characteristics

Physical	Typical Value	Test Method
Specific Gravity	1.445g/cm <sup>3</sup>	ASTM D 792
Mechanical	Typical Value	
Tensile Modulus		
Tensile Strength(Yield)	42.3Mpa	ASTM D638
Flexural Modulus	2779Mpa	ASTM D790
Flexural Strength	74.27Mpa	ASTM D790
Impact	Typical Value	Test Method
Notched Izod Impact-Across Flow 73F (23°C), 0.125 in (3.18mm), Compression Molded Drop Impact Resistance		
73F(23°C)	1.22in.lb/mil	ASTM D4226
73F(23°C)	8.00in.lb/mil	
Hardness	Typical Value	Test Method
Durometer Hardness(Shore D)	80	ASTM D2240
Thermal	Typical Value	Test Method
Deflection Temperature Under Load 264 psi(1.8Mpa),Unannealed,0.125 in (3.18mm)	70 °C	ASTM D648
CLTE-Flow	63.8*10 <sup>-6</sup> 1/°C	ASTM D696
Surface burning characteristics	Typical Value	Test Method
Flame Spread Index	10	ASTM E84
Smoke developed index	400	

PO Box 129 4741 County Road 45 N, Baltimore, Ontario, Canada, K0K 1C0

[structuralpanels.ca/quickliner-plastic-pvc-wall-panels](http://structuralpanels.ca/quickliner-plastic-pvc-wall-panels)

